



Thermory's thermally modified timbers offer a range of natural or pre-finished, ready to install, cladding and lining solutions. Featuring spruce and pine ranges that are responsibly sourced from sustainably grown forests. These timbers are thermally modified using heat and steam, to produce a durable, high performing product range that carries a Class 1 durability rating to perform for decades in Australian conditions.

Thermory modifies the timber for increased durability and dimensional stability in a range of natural and prefinished, ready to install exterior cladding and interior lining solutions.


Spruce Cladding Intense: Natural C26



Main Image: Smooth Face finish. Top Inset Image: Brushed. Bottom Inset Image: Fine Sawn detail.


Texture	Grade	Colour	Species	Size (mm)
Natural Smooth Fine Sawn Brushed	Class 1 Durability Thermally Modified Timber	Golden tones	Spruce	141 x 19

C26 Profile:



■ C26: 141 x 19 / cover: 125mm

Corner Thermo - Spruce CP3



■ 42x42

One universal profile for indoor and outdoor usage. Boards with straight-cut ends can be installed without exposing the endgrain.



CLASS 1



PEFC 21-31-178



Durability
Improved Durability and rot resistance



Stability
Enhanced dimensional stability in changing weather conditions




Chemical-Free
Thermal modification process is entirely natural

Before fixing Thermory claddings, all wall openings, vertical and horizontal joints, sills, heads and corners must be weatherproofed with flashing to comply with National Construction Codes.

Call 1300 399 922
or email info@citytimber.com.au
1400 Centre Rd, Clayton South 3169
citytimber.com.au





DECLARATION OF PERFORMANCE

The undersigned, representing
Thermory AS (Lõõtsa 1a, Tallinn, Harju County, Estonia)
and the manufacturing plant in Loo, Harju County, Estonia
hereby declares that the

THERMALLY MODIFIED SOLID WOOD SPRUCE CLADDING AND PANELING WITHOUT SURFACE COATING

is in conformity with the provisions of the EC Regulation No 305/2011
Construction Product Regulation system of assessment and verification of
constancy of performance: System 3 and is in accordance with the requirements of
EN 14915:2013

„Solid wood panelling and cladding – Characteristics,
evaluation of conformity and marking“
Initial type testing report No.01_THERMORY_EN14915

CHARACTERISTIC	PERFORMANCE DECLARATION
Species	Nordic spruce (<i>Picea abies</i>)
Intended use	For exterior and interior use
Density and range of thickness	400 kg/m ³ , 18–42 mm
Reaction to fire	D-s1, d0 (tested according to standard EN14915:2013)
Emission of formaldehyde	E1
Content of pentachlorophenol	NPD
Release of other dangerous substances	NPD
Water vapor permeability	NPD
Thermal resistance	0,12 W/(m K)
Sound absorption	NPD
Biological durability (according to CEN/TS 15083-1:2005)	Class 1, when thermally modified (215 °C, Intense)